

PRODUCT – SURVEY

WACHS-U. CERESIN-FABRIKEN
TH.C.TROMM
G.M.B.H. KÖLN



WAXES -CATEGORIES

ESTER WAXES

This catalogue shows a range of our waxes and should acquaint the interested user to our production and delivery program. Other special products are available on request. Our Technical Service will provide further information and assist you in case of specific evaluations and solutions.

HARD ESTER WAXES

TYPICAL PROPERTIES

	Drop Point ISO 2176 °C	Acid Value ISO 3682 mg KOH/g	Sapon. Value ISO 3681 mg KOH/g	Colour	Form supplied
Carnicowachs® A-Spezial	90 – 95	2 – 4	19 – 25	light yellow	fine grain
Polycerin® 9548	65 – 72	max. 3	180 – 230	off-white	pellets
Carnicowachs® CLA	62 – 72	12 – 16	45 – 60	light yellow	pellets
Carnicowachs® LT 20	78 – 82	max. 2,5	8 – 15	light yellow	pellets

SOFT ESTER WAXES

TYPICAL PROPERTIES

	Drop Point ISO 2176 °C	Acid Value ISO 3682 mg KOH/g	Sapon. Value ISO 3681 mg KOH/g	Colour	Form supplied
Ceratrom® B-Wax	61 – 65	17 – 21	85 – 95	off-white	pellets
Polycerin® ICS (Japan Wax)	56 – 60	max. 10	105 – 120	off-white	pellets

EMULSIFIER CONTAINING ESTER WAXES

TYPICAL PROPERTIES

	Drop Point ISO 2176 °C	Acid Value ISO 3682 mg KOH/g	Sapon. Value ISO 3681 mg KOH/g	Colour	Form supplied
Carnicowachs® HGZ	78 – 82	5 – 15	60 – 90	yellow/light brown	flakes
TeCe-Wachs® TL 360 E	91 – 99	10 – 15	54 – 64	yellow/light brown	pellets/flakes
Carnicowachs® LT 872	approx. 68	10 – 15	54 – 65	light yellow	pellets
Ceratrom® "Biogade" EH	54 – 61	29 - 42	54 – 64	white /off white	pellets

OXYDIZED WAXES

TYPICAL PROPERTIES

	Drop Point ISO 2176 °C	Acid Value ISO 3682 mg KOH/g	Sapon. Value ISO 3681 mg KOH/g	Colour	Form supplied
TeCe-Wachs® MT 88 S	92 – 99	19 – 26	30 – 45	yellow	fine grain/pellets
TeCe-Wachs® 30 576	102 – 108	14 – 18	-	light yellow	fine grain
TeCe-Wachs® 30 578	98 – 104	23 – 31	-	light yellow	fine grain
TeCe-Wachs® 30 653	97 – 103	26 – 35	-	light yellow	pellets

TH. C. TROMM GMBH

Feuerstr.7-17 D-50735 Köln / Cologne
phone: +49 221 974552-0
e-mail: info@wax-tromm.de

Information and recommendations concerning the use of our products are offered on the understanding that these are to the best of our knowledge. The user is obliged to approve the product to the actual conditions of use. Please note that we cannot undertake any guarantee for the results obtained or for the observance of any existing industrial property rights.