



CANDLE WAXES

This survey shows a range of our waxes and should acquaint the interested user to our production and delivery program. Other special products are available on request. Our Technical Service will provide further information and assist you in case of specific evaluations and solutions.

BEESWAX PURE

TYPICAL PROPERTIES

| Drop Point ISO 2176 °C | Acid Value ISO 3682 mg KOH/g | Sapon. Value ISO 3681 mg KOH/g | Colour | Form supplied |
|------------------------------|------------------------------------|--------------------------------------|--------|---------------|
| 61 - 65 | 17 - 22 | 87 - 102 | white | pellets/slabs |
| 61 - 65 | 17 - 22 | 87 - 102 | yellow | pellets/slabs |

Beeswax 3044 K bleached

Beeswax 3050 A filtered

RAPE SEED WAX

TYPICAL PROPERTIES

| Drop Point ISO 2176 °C | Acid Value ISO 3682 mg KOH/g | Sapon. Value ISO 3681 mg KOH/g | Colour | Form supplied |
|------------------------------|------------------------------------|--------------------------------------|------------|--------------------|
| 52 - 56 | max. 16,5 | 180-200 | off- white | fine grain/pellets |
| 57 - 61 | max. 16,5 | 180-200 | off-white | fine grain/pellets |
| 66 - 72 | max. 16,5 | 180-200 | off-white | fine grain/pellets |

Polycerin® 9512

Polycerin® 9562

Polycerin® 9522

STEARIC ACID

TYPICAL PROPERTIES

| Drop Point ISO 2176 °C | Acid Value ISO 3682 mg KOH/g | Sapon. Value ISO 3681 mg KOH/g | Colour | Form supplied |
|------------------------------|------------------------------------|--------------------------------------|------------|--------------------|
| 57 - 61 | 195-210 | 195-210 | off- white | fine grain/pellets |

TeCe-Stearin white I

HYDROCARBON WAX

TYPICAL PROPERTIES

| Drop Point ISO 2176 °C | Penetration DIN 51579 0,1mm/25°C | Viscosity DIN 53019 cps/100°C | Colour | Form supplied |
|------------------------------|--|-------------------------------------|--------------|---------------|
| 52 - 56 | 15 - 19 | 2 - 4 | off-white | slabs/pellets |
| 55 - 60 | 14 - 19 | 2 - 4 | off-white | slabs/pellets |
| 76 - 82 | 23 - 28 | 10 - 14 | white/yellow | slabs |
| 99 - 105 | 4 - 7 | 7-11 (120°C) | white | pellets |
| 58 - 62 | 15 - 22 | 5 - 7 | off-white | pellets |

Polarit® 30 227

Polarit® 30 731

TeCero-Wachs® 2004 K

TeCero-Wachs® 6004 K

TeCe-Ceresin® G 60

NEUTRAL WAXES

TYPICAL PROPERTIES

| Drop Point ISO 2176 °C | Penetration DIN 51579 0,1mm/25°C | Viscosity DIN 53019 cps/100°C | Colour | Form supplied |
|------------------------------|--|-------------------------------------|-----------|---------------|
| 73 - 78 | 15 - 19 | 10 - 12 | off-white | pellets |
| 92 - 97 | 1 | 165 - 185 | off-white | fine grain |
| 89 - 95 | 7 - 12 | 100 - 200 | off-white | pellets |

TeCero-Wachs® TL 290

Polycerit® N 281

Cerathen® N 450

TH. C. TROMM GMBH

Feuerstr.7-17 D-50735 Köln / Cologne

phone: +49 221 974552-0

e-mail: info@wax-tromm.de

Information and recommendations concerning the use of our products are offered on the understanding that these are to the best of our knowledge. The user is obliged to approve the product to the actual conditions of use. Please note that we cannot undertake any guarantee for the results obtained or for the observance of any existing industrial property rights.