

PRODUCT - SURVEY

WAXES - APPLICATION

WACHS- U. CERESIN-FABRIKEN
TH.C.TROMM
G.M.B.H.KÖLN



EMULSION

This survey shows a range of our waxes and should acquaint the interested user to our production and delivery program. Other special products are available on request. Our Technical Service will provide further information and assist you in case of specific evaluations and solutions.

NATURAL WAXES

TYPICAL PROPERTIES

Drop Point ISO 2176 °C	Acid Value ISO 3682 mg KOH/g	Sapon.Value ISO 3681 mg KOH/g	Colour	Form supplied
61 - 65	17 - 22	87 - 102	white	pellets/slabs
61 - 65	17 - 22	87 - 102	yellow	pellets/slabs
81 - 86	2 - 7	80 - 95	light yellow	flakes
81 - 86	2 - 7	80 - 95	yellow	flakes

Beeswax 3044 K bleached

Beeswax 3050 A filtered

Carnaubawax LT 124

Carnaubawax LT 314

HYDROCARBON WAXES

TYPICAL PROPERTIES

Drop Point ISO 2176 °C	Penetration DIN 51579 0,1mm/25°C	Viscosity DIN 53019 cps/100°C	Colour	Form supplied
52 - 56	15 - 19	2 - 4	off-white	slabs/pellets
55 - 60	14 - 19	2 - 4	off-white	slabs/pellets

Polarit® 30 227

Polarit® 30 731

EMULSIFIER CONTAINING ESTER WAXES

TYPICAL PROPERTIES

Drop Point ISO 2176 °C	Acid Value ISO 3682 mg KOH/g	Sapon.Value ISO 3681 mg KOH/g	colour	Form supplied
78 - 82	5 - 15	60 - 90	yellow/light brown	flakes
91 - 99	10 - 15	54 - 64	yellow/light brown	pellets/flakes

Carnicowachs® HGZ

TeCe-Wachs® TL 360 E

OXYDIZED WAXES

TYPICAL PROPERTIES

Drop Point ISO 2176 °C	Acid Value ISO 3682 mg KOH/g	Sapon.Value ISO 3681 mg KOH/g	Colour	Form supplied
102 - 108	14 - 18	-	light yellow	fine grain
98 - 104	23 - 31	-	light yellow	fine grain
97 - 103	26 - 35	-	light yellow	pellets

TeCe-Wachs® 30 576

TeCe-Wachs® 30 578

TeCe-Wachs® 30 653

TH. C. TROMM GMBH

Feuerstr.7-17 D-50735 Köln / Cologne
phone: +49 221 974552-0
e-mail: info@wax-tromm.de

Information and recommendations concerning the use of our products are offered on the understanding that these are to the best of our knowledge. The user is obliged to approve the product to the actual conditions of use. Please note that we cannot undertake any guarantee for the results obtained or for the observance of any existing industrial property rights.