



## PRODUCT – SURVEY

### WAXES -CATEGORIES

#### ESTER WAXES

This catalogue shows a range of our waxes and should acquaint the interested user to our production and delivery program. Other special products are available on request. Our Technical Service will provide further information and assist you in case of specific evaluations and solutions.

#### HARD ESTER WAXES

##### TYPICAL PROPERTIES

	Drop Point ISO 2176 °C	Acid Value ISO 3682 mg KOH/g	Sapon.Value ISO 3681 mg KOH/g	Colour	Form supplied
<b>Carnicowachs® A-Spezial</b>	90 – 95	2 – 4	19 – 25	light yellow	fine grain
<b>Polycerin® 9548</b>	65 – 72	max. 3	180 – 230	off-white	pellets
<b>Carnicowachs® CLA</b>	62 – 72	12 – 16	45 – 60	light yellow	pellets
<b>Carnicowachs® LT 20</b>	78 – 82	max. 2,5	8 – 15	light yellow	pellets

#### SOFT ESTER WAXES

##### TYPICAL PROPERTIES

	Drop Point ISO 2176 °C	Acid Value ISO 3682 mg KOH/g	Sarpan.Value ISO 3681 mg KOH/g	Colour	Form supplied
<b>Ceratrom® B-Wax</b>	61 – 65	17 – 21	85 – 95	off-white	pellets
<b>Polycerin® ICS (Japan Wax)</b>	56 – 60	max. 10	105 – 120	off-white	pellets

#### EMULSIFIER CONTAINING ESTER WAXES

##### PROPERTIES

##### TYPICAL

	Drop Point ISO 2176 °C	Acid Value ISO 3682 mg KOH/g	Sapon.Value ISO 3681 mg KOH/g	Colour	Form supplied
<b>Carnicowachs® HGZ</b>	78 – 82	5 – 15	60 – 90	yellow/light brown	flakes
<b>TeCe-Wachs® TL 360 E</b>	91 – 99	10 – 15	54 – 64	yellow/light brown	pellets/flakes
<b>Carnicowachs® LT 872</b>	approx. 68	10 – 15	54 – 65	light yellow	pellets
<b>Ceratrom® "Biogade" EH</b>	54 – 61	29 - 42	54 – 64	white /off white	pellets

#### OXYDIZED WAXES

##### TYPICAL PROPERTIES

	Drop Point ISO 2176 °C	Acid Value ISO 3682 mg KOH/g	Sapon.Value ISO 3681 mg KOH/g	Colour	Form supplied
<b>TeCe-Wachs® MT 88 S</b>	92 – 99	19 – 26	30 – 45	yellow	fine grain/pellets
<b>TeCe-Wachs® 30 576</b>	102 – 108	14 – 18	-	light yellow	fine grain
<b>TeCe-Wachs® 30 578</b>	98 – 104	23 – 31	-	light yellow	fine grain
<b>TeCe-Wachs® 30 653</b>	97 – 103	26 – 35	-	light yellow	pellets

#### TH. C. TROMM GMBH

Feuerstr.7-17 D-50735 Köln / Cologne  
 phone: +49 221 974552-0  
 e-mail: [info@wax-tromm.de](mailto:info@wax-tromm.de)

Information and recommendations concerning the use of our products are offered on the understanding that these are to the best of our knowledge. The user is obliged to approve the product to the actual conditions of use. Please note that we cannot undertake any guarantee for the results obtained or for the observance of any existing industrial property rights.