

PRODUCT – SURVEY

WAXES - APPLICATION

WACHS- U. CERESIN-FABRIKEN
TH.C.TROMM
G.M.B.H.KÖLN



HOUSEHOLD CARE AND MAINTENANCE PRODUCTS

This survey shows a range of our waxes and should acquaint the interested user to our production and delivery program. Other special products are available on request. Our Technical Service will provide further information and assist you in case of specific evaluations and solutions.

NATURAL WAXES

TYPICAL PROPERTIES

	Drop Point ISO 2176 °C	Acid Value ISO 3682 mg KOH/g	Sapon.Value ISO 3681 mg KOH/g	Colour	Form supplied
Beeswax 3044 K bleached	61 - 65	17 – 22	87 –102	white	pellets/slabs
Beeswax 3050 A filtered	61 - 65	17 – 22	87 –102	yellow	pellets/slabs
Carnaubawax LT 124	81 - 86	2 – 7	80 – 95	light yellow	flakes
Carnaubawax LT 314	81 - 86	2 – 7	80 – 95	yellow	flakes

HYDROCARBON WAXES

TYPICAL PROPERTIES

	Drop Point ISO 2176 °C	Penetration DIN 51579 0,1mm/25°C	Viscosity DIN 53019 cps/100°C	Colour	Form supplied
Polarit® 30 227	52 – 56	15 – 19	2 – 4	off-white	slabs/pellets
Polarit® 30 731	55 - 60	14 - 19	2 - 4	off-white	slabs/pellets
TeCero-Wachs® 2004 K	76 - 82	23 – 28	10 – 14	white/yellow	slabs
TeCero-Wachs® 5004 K	68 - 72	15 - 22	10 - 14	off-white	slabs/pellets
Polarwachs® C 324	105 – 115	2 – 5	70-110 (150°C)	off white	pellets
Polarwachs® H 990 M	98 - 106	6 - 9	18 - 23	white	fine grain

EMULSIFIER CONTAINING ESTER WAXES

TYPICAL PROPERTIES

	Drop Point ISO 2176 °C	Acid Value ISO 3682 mg KOH/g	Sapon.Value ISO 3681 mg KOH/g	colour	Form supplied
Carnicowachs® HGZ	78 – 82	5 – 15	60 – 90	yellow/light brown	flakes
TeCe-Wachs® TL 360 E	91 – 99	10 – 15	54 – 64	yellow/light brown	pellets/flakes

TH. C. TROMM GMBH

Feuerstr.7-17 D-50735 Köln / Cologne
phone: +49 221 974552-0
e-mail: info@wax-tromm.de

Information and recommendations concerning the use of our products are offered on the understanding that these are to the best of our knowledge. The user is obliged to approve the product to the actual conditions of use. Please note that we cannot undertake any guarantee for the results obtained or for the observance of any existing industrial property rights.