

# PRODUCT – SURVEY

## WAXES - CATEGORIES

WACHS-U. CERESIN-FABRIKEN  
**TH.C.TROMM**  
G.M.B.H.KÖLN



### HYDROCARBON WAXES

This survey shows a range of our waxes and should acquaint the interested user to our production and delivery program. Other special products are available on request. Our Technical Service will provide further information and assist you in case of specific evaluations and solutions.

### SPECIAL PARAFFIN

#### TYPICAL PROPERTIES

Drop Point ISO 2176 °C	Penetration DIN 51579 0,1mm/25°C	Viscosity DIN 53019 cps/100°C	Colour	Form supplied
------------------------------	--	-------------------------------------	--------	---------------

<b>Polarit® 30 227</b>	52 – 56	15 – 19	2 – 4	off-white	slabs/pellets
<b>Polarit® 30 731</b>	55 - 60	14 - 19	2 - 4	off-white	slabs/pellets
<b>Polarit® 30 789</b>	60 – 62	12 - 17	3 – 5	off-white	slabs/pellets
<b>Polarit® 30 768</b>	64 – 66	12 - 17	2 – 6	off-white	slabs/pellets

### MICROCRYSTALLINE WAX

#### TYPICAL PROPERTIES

Drop Point ISO 2176 °C	Penetration DIN 51579 0,1mm/25°C	Viscosity DIN 53019 cps/100°C	Colour	Form supplied
------------------------------	--	-------------------------------------	--------	---------------

<b>TeCero-Wachs® 1030 K</b>	68 - 72	15 - 22	7 - 10	off-white	pellets
<b>TeCero-Wachs® 2004 K</b>	76 - 82	23 – 28	10 – 14	white/yellow	slabs
<b>TeCero-Wachs® 3004 K</b>	80 - 88	15 - 20	10 - 14	off-white	slabs/pellets
<b>TeCero-Wachs® 5004 K</b>	68 - 72	15 - 22	10 - 14	off-white	slabs/pellets
<b>TeCero-Wachs® 6004 K</b>	99 -105	4 - 7	120°C: 7–11	white	pellets

### OZOKERITE/CERESIN

#### TYPICAL PROPERTIES

Drop Point ISO 2176 °C	Penetration DIN 51579 0,1mm/ 25°C	Viscosity DIN 53019 cps/100°C	Color	Form supplied
------------------------------	---	-------------------------------------	-------	---------------

<b>TeCe-Ozokerit® H 502</b>	68 - 72	15 - 22	7 - 10	white	pellets
<b>TeCe-Ozokerit® HH 680</b>	90 - 94	5 - 11	10 - 14	white	pellets
<b>TeCe-Ceresin® N 662</b>	64 - 69	15 - 20	7 - 10	off-white	pellets
<b>TeCe-Ceresin® G 70</b>	68 - 72	15 - 22	5 – 9	off-white	pellets
<b>TeCe-Ceresin® G 60</b>	58 - 62	15 - 22	5 – 7	off-white	pellets

#### TH. C. TROMM GMBH

Feuerstr.7-17 D-50735 Köln / Cologne  
phone: +49 221 974552-0  
e-mail: [info@wax-tromm.de](mailto:info@wax-tromm.de)

Information and recommendations concerning the use of our products are offered on the understanding that these are to the best of our knowledge. The user is obliged to approve the product to the actual conditions of use. Please note that we cannot undertake any guarantee for the results obtained or for the observance of any existing industrial property rights.