

# PRODUCT - SURVEY

## WAXES - CATEGORIES

WACHS- U. CERESIN-FABRIKEN  
**TH.C.TROMM**  
G.M.B.H.KÖLN



### NEUTRAL WAXES

This survey shows a range of our waxes and should acquaint the interested user to our production and delivery program. Other special products are available on request. Our Technical Service will provide further information and assist you in case of specific evaluations and solutions.

### NEUTRAL HARD WAXES

#### TYPICAL PROPERTIES

	Drop Point ISO 2176 °C	Penetration DIN 51579 0,1mm/25°C	Viscosity DIN 53019 cps/120°C	Colour	Form supplied
<b>Polarwachs® C 324</b>	105 – 115	2 – 5	70-110 (150°C)	off white	pellets
<b>Polarwachs® TL 352</b>	95 - 101	5 – 9	max. 10	white	fine grain
<b>Polarwachs® 30 755</b>	114 - 120	max. 2	5 - 15	white	fine grain
<b>Polarwachs® H 990 M</b>	98 - 106	6 - 9	18 - 23	white	fine grain
<b>Polycerit® N 281</b>	92 - 97	1	165 - 185	off-white	fine grain

### POLYMER WAXES

#### TYPICAL PROPERTIES

	Drop Point ISO 2176 °C	Penetration DIN 51579 0,1mm/25°C	Viscosity DIN 53019 cps/100°C	Colour	Form supplied
<b>Polycerit® CAT</b>	46 - 55	8 - 12	260 - 360	off white	pellets
<b>Polycerit® FAT</b>	65 - 75	2 - 5	220 - 360	white	pellets
<b>TeCero-Wachs® TOP 08</b>	60 - 65	2 - 5	15 - 21	white	pellets
<b>Polycerit® W</b>	100 - 110	2 - 5	2000-5000 (120°C)	white	granulated
<b>Polycerit® PT 90 LF</b>	155 - 160	max. 1	500-2000 (180°C)	off-white	fine grain

### SPECIAL WAX BLENDS

#### TYPICAL PROPERTIES

	Drop Point ISO 2176 °C	Penetration DIN 51579 0,1mm/25°C	Viscosity DIN 53019 cps/100°C	Colour	Form supplied
<b>TeCero-Wachs® TL 290</b>	73 – 78	15 – 19	10 - 12	off-white	pellets
<b>TeCero-Wachs® TL 109</b>	80 – 84	30 – 40	25 - 35	yellow	slabs
<b>Cerathen® GC 80</b>	78 – 85	8 –11	2800 - 3200	off-white	pellets
<b>Cerathen® N 450</b>	89 – 95	7 –12	100 - 200	off-white	pellets

**TH. C. TROMM GMBH**  
Feuerstr.7-17 D-50735 Köln / Cologne  
phone: +49 221 974552-0  
e-mail: [info@wax-tromm.de](mailto:info@wax-tromm.de)

Information and recommendations concerning the use of our products are offered on the understanding that these are to the best of our knowledge. The user is obliged to approve the product to the actual conditions of use. Please note that we cannot undertake any guarantee for the results obtained or for the observance of any existing industrial property rights.