

# PRODUCT – SURVEY

## WAXES - APPLICATION

WACHS- U. CERESIN-FABRIKEN  
**TH.C.TROMM**  
G.M.B.H.KÖLN



### PAPER AND FOIL CONVERTING

This survey shows a range of our waxes and should acquaint the interested user to our production and delivery program. Other special products are available on request. Our Technical Service will provide further information and assist you in case of specific evaluations and solutions.

### SPECIAL PARAFFIN

#### TYPICAL PROPERTIES

Drop Point ISO 2176 °C	Penetration DIN 51579 0,1mm/25°C	Viscosity DIN 53019 cps/100°C	Colour	Form supplied	
Polarit® 30 227	52 – 56	15 – 19	2 – 4	off-white	slabs/pellets
Polarit® 30 731	55 - 60	14 - 19	2 - 4	off-white	slabs/pellets
Polarit® 30 789	60 – 62	12 - 17	3 – 5	off-white	slabs/pellets
Polarit® 30 768	64 – 66	12 - 17	2 – 6	off-white	slabs/pellets

### NEUTRAL HARD WAXES

#### TYPICAL PROPERTIES

Drop Point ISO 2176 °C	Penetration DIN 51579 0,1mm/25°C	Viscosity DIN 53019 cps/120°C	Colour	Form supplied	
Polarwachs® H 990 M	98 - 106	6 - 9	18 - 23	white	fine grain
Polycerit® N 281	92 - 97	1	165 - 185	off-white	fine grain

### SPECIAL WAX BLENDS

#### TYPICAL PROPERTIES

Drop Point ISO 2176 °C	Penetration DIN 51579 0,1mm/25°C	Viscosity DIN 53019 cps/100°C	Colour	Form supplied	
TeCero-Wachs® TL 109	80 – 84	30 – 40	25 - 35	yellow	slabs
Cerathen® GC 80	78 – 85	8 –11	2800 - 3200	off-white	pellets
Cerathen® N 450	89 – 95	7 –12	100 - 200	off-white	pellets

#### TH. C. TROMM GMBH

Feuerstr.7-17 D-50735 Köln / Cologne  
phone: +49 221 974552-0  
e-mail: [info@wax-tromm.de](mailto:info@wax-tromm.de)

Information and recommendations concerning the use of our products are offered on the understanding that these are to the best of our knowledge. The user is obliged to approve the product to the actual conditions of use. Please note that we cannot undertake any guarantee for the results obtained or for the observance of any existing industrial property rights.