

PRODUCT – SURVEY

WAXES - APPLICATION

WACHS- U. CERESIN-FABRIKEN
TH.C.TROMM
G.M.B.H.KÖLN



RUBBER / PLASTIC PROCESSING

This survey shows a range of our waxes and should acquaint the interested user to our production and delivery program. Other special products are available on request. Our Technical Service will provide further information and assist you in case of specific evaluations and solutions.

SPECIAL PARAFFIN

TYPICAL PROPERTIES

Drop Point ISO 2176 °C	Penetration DIN 51579 0,1mm/25°C	Viscosity DIN 53019 cps/100°C	Colour	Form supplied
------------------------------	--	-------------------------------------	--------	---------------

Polarit® 30 227	52 – 56	15 – 19	2 – 4	off-white	slabs/pellets
Polarit® 30 731	55 - 60	14 - 19	2 - 4	off-white	slabs/pellets
Polarit® 30 789	60 – 62	12 - 17	3 – 5	off-white	slabs/pellets
Polarit® 30 768	64 – 66	12 - 17	2 – 6	off-white	slabs/pellets

CERESIN

TYPICAL PROPERTIES

Drop Point ISO 2176 °C	Penetration DIN 51579 0,1mm/ 25°C	Viscosity DIN 53019 cps/100°C	Color	Form supplied
------------------------------	---	-------------------------------------	-------	---------------

TeCe-Ceresin® G 70	68 - 72	15 - 22	5 – 9	off-white	pellets
TeCe-Ceresin® G 60	58 - 62	15 - 22	5 – 7	off-white	pellets

NEUTRAL HARD WAXES

TYPICAL PROPERTIES

Drop Point ISO 2176 °C	Penetration DIN 51579 0,1mm/25°C	Viscosity DIN 53019 cps/120°C	Colour	Form supplied
------------------------------	--	-------------------------------------	--------	---------------

Polarwachs® H 990 M	98 - 106	6 - 9	18 - 23	white	fine grain
Polycerit® N 281	92 - 97	1	165 - 185	off-white	fine grain

ESTER WAXES

TYPICAL PROPERTIES

Drop Point ISO 2176 °C	Acid Value ISO 3682 mg KOH/g	Sapon.Value ISO 3681 mg KOH/g	Colour	Form supplied
------------------------------	------------------------------------	-------------------------------------	--------	---------------

Carnicowachs® LT 20	78 – 82	max. 2,5	8 – 15	light yellow	pellets
Polycerin® 9548	65 – 72	max. 3	180 – 230	off-white	pellets

TH. C. TROMM GMBH
Feuerstr.7-17 D-50735 Köln / Cologne
phone: +49 221 974552-0
e-mail: info@wax-tromm.de

Information and recommendations concerning the use of our products are offered on the understanding that these are to the best of our knowledge. The user is obliged to approve the product to the actual conditions of use. Please note that we cannot undertake any guarantee for the results obtained or for the observance of any existing industrial property rights.