

# PRODUCT – SURVEY

## WAXES - APPLICATION

WACHS- U. CERESIN-FABRIKEN  
**TH.C.TROMM**  
G.M.B.H.KÖLN



### RUBBER / PLASTIC PROCESSING

This survey shows a range of our waxes and should acquaint the interested user to our production and delivery program. Other special products are available on request. Our Technical Service will provide further information and assist you in case of specific evaluations and solutions.

### SPECIAL PARAFFIN

#### TYPICAL PROPERTIES

Drop Point ISO 2176 °C	Penetration DIN 51579 0,1mm/25°C	Viscosity DIN 53019 cps/100°C	Colour	Form supplied
------------------------------	--	-------------------------------------	--------	---------------

**Polarit® 30 227**

52 – 56      15 – 19      2 – 4      off-white      slabs/pellets

**Polarit® 30 731**

55 - 60      14 - 19      2 - 4      off-white      slabs/pellets

**Polarit® 30 789**

60 – 62      12 - 17      3 – 5      off-white      slabs/pellets

**Polarit® 30 768**

64 – 66      12 - 17      2 – 6      off-white      slabs/pellets

### CERESIN

#### TYPICAL PROPERTIES

Drop Point ISO 2176 °C	Penetration DIN 51579 0,1mm/ 25°C	Viscosity DIN 53019 cps/100°C	Color	Form supplied
------------------------------	---	-------------------------------------	-------	---------------

**TeCe-Ceresin® G 70**

68 - 72      15 - 22      5 – 9      off-white      pellets

**TeCe-Ceresin® G 60**

58 - 62      15 - 22      5 – 7      off-white      pellets

### NEUTRAL HARD WAXES

#### TYPICAL PROPERTIES

Drop Point ISO 2176 °C	Penetration DIN 51579 0,1mm/25°C	Viscosity DIN 53019 cps/120°C	Colour	Form supplied
------------------------------	--	-------------------------------------	--------	---------------

**Polarwachs® H 990 M**

98 - 106      6 - 9      18 - 23      white      fine grain

**Polycerit® N 281**

92 - 97      1      165 - 185      off-white      fine grain

### ESTER WAXES

#### TYPICAL PROPERTIES

Drop Point ISO 2176 °C	Acid Value ISO 3682 mg KOH/g	Sapon.Value ISO 3681 mg KOH/g	Colour	Form supplied
------------------------------	------------------------------------	-------------------------------------	--------	---------------

**Carnicowachs® LT 20**

78 – 82      max. 2,5      8 – 15      light yellow      pellets

**Polycerin® 9548**

65 – 72      max. 3      180 – 230      off-white      pellets

### TH. C. TROMM GMBH

Feuerstr.7-17 D-50735 Köln / Cologne  
phone: +49 221 974552-0  
e-mail: [info@wax-tromm.de](mailto:info@wax-tromm.de)

Information and recommendations concerning the use of our products are offered on the understanding that these are to the best of our knowledge. The user is obliged to approve the product to the actual conditions of use. Please note that we cannot undertake any guarantee for the results obtained or for the observance of any existing industrial property rights.