

# PRODUCT - SURVEY

## WAXES - APPLICATION

WACHS- U. CERESIN-FABRIKEN  
**TH.C.TROMM**  
G.M.B.H.KÖLN



### COSMETICS PHARMACEUTICALS

This survey shows a range of our waxes and should acquaint the interested user to our production and delivery program. Other special products are available on request. Our Technical Service will provide further information and assist you in case of specific evaluations and solutions.

### ESTER WAXES

#### TYPICAL PROPERTIES

	Drop Point ISO 2176 °C	Acid Value ISO 3682 mg KOH/g	Saponf. Value ISO 3681 mg KOH /g	Colour	Form supplied
Beeswax 3044 PH bleached	61 – 65	17 – 22	87 –102	white	pellets/slabs
Beeswax 3046 PH bleached	61 – 65	17 – 22	87 –102	ivory	pellets/slabs
Beeswax 3050 PH filtered	61 – 65	17 – 22	87 –102	yellow	pellets/slabs
Beeswax 3055 PH filtered	61 – 65	17 – 22	87 –102	yellow	pellets/slabs
Carnaubawax LT 124	81 – 86	2 – 7	80 – 95	light yellow	flakes
Ceratrom® B-Wax	61 – 65	17 - 21	85 -95	light amber	pellets
Ceratrom® ICS	56 – 61	max.10	105-120	off-white	pellets
Carnicowachs® LT 20	78 – 82	max. 2,5	8 – 15	light yellow	pellets
Carnicowachs® CLA	76 – 80	12 – 16	45 – 60	light yellow	pellets
Ceratrom® "Biogade" EH	54 – 61	29 – 42	54 – 64	white /off white	pellets
Carnicowachs® LT 872	approx. 68	10 – 15	54 – 65	light yellow	pellets

### NEUTRAL WAXES

#### TYPICAL PROPERTIES

	Drop Point ISO 2176 °C	Viscosity DIN 53019 mPas/100°C	Penetration DIN 51579 0,1mm/25°C	Colour	Form supplied
TeCe-Ozokerit® H 502	74 - 78	-	15 – 22	white	slabs
TeCe-Ozokerit® HH 680	66 - 92	-	5 – 11	white/amber	slabs/pellets
TeCe-Ceresin® N 662	64 - 69	15 - 20	7 – 10	off-white	pellets
TeCero-Wachs® 1030 K	68 - 72	15 - 22	7 – 10	off-white	pellets
TeCero-Wachs® 2004 K	76 - 82	10 – 14	23 – 28	off-white	pellets
TeCero-Wachs® 6004 K	99 -105	7 -11 (120°C)	4 – 7	white	pellets

#### TH. C. TROMM GMBH

Feuerstr.7-17 D-50735 Köln / Cologne  
phone: +49 221 974552-0  
e-mail: [info@wax-tromm.de](mailto:info@wax-tromm.de)

Information and recommendations concerning the use of our products are offered on the understanding that these are to the best of our knowledge. The user is obliged to approve the product to the actual conditions of use. Please note that we cannot undertake any guarantee for the results obtained or for the observance of any existing industrial property rights.